

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Urkunde Certificate Certificat

Es wird hiermit bescheinigt, daß für die in der beigefügten Patentschrift beschriebene Erfindung ein europäisches Patent für die in der Patentschrift bezeichneten Vertragsstaaten erteilt worden ist.

It is hereby certified that a European patent has been granted in respect of the invention described in the annexed patent specification for the Contracting States designated in the specification.

Il est certifié qu'un brevet européen a été délivré pour l'invention décrite dans le fascicule de brevet ci-joint, pour les Etats contractants désignés dans le fascicule de brevet.

Europäisches Patent Nr.

European Patent No.

Brevet européen n°

0623005

Patentinhaber

Proprietor of the Patent

Titulaire du brevet

BIOCON OY
Runeberginkatu 3 A 1
33710 Tampere/FI

München, den
Munich,
Fait à Munich, le

14.04.99

Ingo Kober

Präsident des Europäischen Patentamts
President of the European Patent Office
Président de l'Office européen des brevets

THIS PAGE BLANK (USPTO)

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 623 005 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

14.04.1999 Bulletin 1999/15

(21) Application number: 93902269.5

(22) Date of filing: 18.01.1993

(51) Int. Cl.⁶: **A61B 17/064**, A61B 17/56

(86) International application number:
PCT/FI93/00014

(87) International publication number:
WO 93/14705 (05.08.1993 Gazette 1993/19)

(54) SURGICAL IMPLANT

CHIRURGISCHES IMPLANTAT

IMPLANT CHIRURGICAL

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB IT LI NL SE

(30) Priority: 24.01.1992 FI 920305

(43) Date of publication of application:
09.11.1994 Bulletin 1994/45

(73) Proprietor: BIOCON OY
33710 Tampere (FI)

(72) Inventors:
• TAMMINMÄKI, Markku
SF-33400 Tampere (FI)

- KRISTENSEN, Gert
DK-8400 Ebeltøft (DK)
- ALBRECHT-OLSEN, Peter
DK-2920 Charlottenlund (DK)
- TÖRMÄLÄ, Pertti
SF-33710 Tampere (FI)

(74) Representative:
Joly, Jean-Jacques et al
Cabinet Beau de Loménie
158, rue de l'Université
75340 Paris Cédex 07 (FR)

(56) References cited:
US-A- 4 873 976

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a surgical implant formed in the shape of an arrow comprising a body whose first end is formed as a stem and whose second end is formed as a head with arresting means intended for arresting the implant in a position according to the use of the implant particularly in a direction opposite to the direction of installation, wherein the stem protrudes from the outer surface of the body and wherein the implant is manufactured of a polymer or a polymeric compound which is substantially absorbable in tissue conditions and contains reinforcing structure or the like, also of a polymer or a polymeric compound.

[0002] The surgical implant of the invention is particularly but not solely intended to be used in repair surgery of traumas of soft and/or tough tissues containing fibrous structures, such as meniscal tissues.

[0003] With reference to the prior art in the field it has been shown that fixation of meniscus traumas like ruptures and lesions by suturing with absorbable sutures gives better results than the removal of traumatized meniscal tissue (see e.g. N.A. Palmeri, T.F. Winters, A.E. Joiner and T. Evans, "The Development and Testing of the Arthroscopic Meniscal Staple", *Arthroscopy*, Vol. 5, No. 2, 1989, p. 156 (Ref. 1)). However, arthroscopic suturing is a complicated technique where risks for the patient are significant e.g. because of danger to vessels and nerves. Therefore, the desire of surgeons has been already for a long time to have an absorbable meniscus lesion fixation device like a staple or fastener which should have the advantages of absorbable suturing techniques but which should be more rapid to use and without complications of suture technique.

[0004] Several research groups have tried to develop absorbable meniscus lesion fixation devices like clamps or the like. However, the demands of such a device are high. It must be strong enough to maintain the good contact of lesion tissues after operation so that rapid healing occurs. The device must retain its strength long enough for good healing. It must be biocompatible and it must be absorbed without causing complications which should prevent the healing of lesion. Additionally, the installation of the device should be easy and rapid and should cause minimum operational trauma. Because of those high demands, a satisfactory, absorbable meniscus lesion fixation device has not been developed yet. Palmeri et al. reported in Ref. 1 the development of a methods of meniscal repair using arthroscopically applied absorbable fasteners. However, the reported method was complicated because the final design used cannulation of the staple for needle-guided placement. Additionally staple fracture, migration and articular abrasion was found.

[0005] With regard to implants known in this field, reference is made to US-4,873,976 which discloses an arrow-like implant, having a basic structure that can be identified with the preamble of claim 1, particularly for

repair surgery of meniscal rupture. However, the arrow-like implant according to the publication has the disadvantage that particularly its stem is shaped as a plate in a way that the direction of the main plane of the plate is perpendicular to the longitudinal direction of the body. Because of this fact, it is particularly difficult to install the implant, because the installation channel to be used in connection with installing the implant must be formed to have the cross-sectional shape of the stem; it is difficult to guide the implant in the installation channel, because the guiding effect is substantially brought upon the stem only. Furthermore, due to the structure of the stem, it causes mechanical irritation and abrasion of the tissue particularly when placed in connection with the meniscus, because the stem is usually left protruding even to a high degree from the outer surface of the meniscus.

[0006] In this invention, it has been unexpectedly found that by designing a surgical implant of the invention according to the characterising part of claim 1 mainly by forming the stem substantially of at least one wing extending in the longitudinal direction of the body, which is at one edge connected to the body, and preferably by forming the arresting means at least partially by machining the material, e.g. by cutting the material of the body in a direction substantially parallel and/or diagonal to the body, an implant is obtained which is substantially both effective in the installation situation in connection with a surgical operation and causes as little tissue irritation in the soft and/or tough tissue after the installation. Particularly but not solely in the surgical treatment of ruptures or other damage of the meniscus, the placement of the stem essentially in the longitudinal direction of the body provides the advantage that although part of the stem remains at the surface of the meniscus when the implant is installed, the wing form is placed substantially in the direction of the meniscus, whereby there is very little tissue irritation by protruding parts. Another advantage is provided by the fact that the stem is arranged substantially in the longitudinal direction of the body and preferably also has a maximum thickness equal to the diameter of the body in the direction of the thickness, namely that the installation channel of the installation instrument can be shaped so that the implant receives its guidance during the installation stage of the surgical operation on all the length of the body. The surgeon can thus install the implant with maximum security so that it is placed in the position intended for it in the right direction.

[0007] Some advantageous embodiments of the invention are described in the appended dependent claims. As to the advantages obtained by them, reference is made to the description below.

[0008] The present invention will be more fully described in the following description with reference to the appended drawings. In the drawings,

Fig. 1 shows a perspective view of an embodiment of the surgical implant according to

the invention, and

Figs. 2-5 show sectional views of the meniscus, in which one or several surgical implants according to the invention have been installed.

[0009] The implants according to the invention are manufactured of polymeric self-reinforced absorbable composites (SRAC) which have been described in several publications, including U.S. Pat. No. 4,743,257 and Finnish Pat. Appl. No. 870111. The bone fracture fixation devices manufactured of polymeric SRAC are known from earlier. However, in the meniscal repair surgery, the SRAC materials are not previously known. Here we have unexpectedly found that regardless of the totally different nature of meniscal tissue (fibrous, soft, tough and elastic) in comparison with bone tissue (hard and brittle), the meniscal repair devices made of SRAC give good fixation of meniscal lesions. Additionally, SRAC meniscal fixation devices are rapid and safe to use with a special instrument related to this invention and described in a parallel application, which is of significant benefit for surgical practice (PCT/FI93/00015).

[0010] Polymeric SRAC is the ideal raw material in manufacturing of devices of this invention because of several reasons:

- meniscal lesion fixation devices made of SRAC are strong, tough and stiff structures so that they can be triggered with a special instrument to penetrate into the meniscal tissue, traverse the rupture or lesion and penetrate also to the meniscal tissue on the other side of rupture or lesion without the need to use some kind of auxiliary guides like needles, cannulated tubes etc. like in the earlier known techniques,
- the strong SRAC devices maintain the ruptured meniscal parts in contact with each other during the early period of healing leading to a rapid consolidation of the lesion or rupture in the tissue, and
- the absorption of SRAC implant guarantees that after absorption there is no risk of implant related long term complications, such as inflammatory reactions or infections which may occur with biostable polymeric implants even years after operation.

[0011] Partially crystalline, absorbable polymers, copolymers or polymer mixtures or alloys are especially suitable raw materials for manufacturing of the implant of this invention. Some suitable polymers that can be used as materials for the implant include polymers known from the following publications:

U.S. Patent S.N. 4,700,704; U.S. Patent S.N. 4,653,497, U.S. Patent S.N. 4,649,921; U.S. Patent S.N. 4,559,945, U.S. Patent S.N. 4,532,928; U.S. Patent S.N. 4,605,730, U.S. Patent S.N. 4,441,496; U.S. Patent S.N. 4,435,590.

[0012] The implants of the invention can be manufactured of the above polymers by applying either one polymer or a suitable polymer alloy or mixture.

[0013] Figure 1 shows a typical surgical implant according to the invention. It is designed to have an arrow shape, and it comprises a body 1 whose one end is formed as a stem 2 and whose other end is formed as the head 3. The head comprises arresting means 5 extending to the section of the body 1. The purpose of the stem 2 is to stop the implant at the final stage of the installation and to prevent the implant from moving in the direction of installation when it is in the installed position. The arresting means 5 are intended to keep the implant installed in the position of use, particularly in the direction opposite to the direction of installation. Thus, the stem 2 protrudes from the outer surface of the body 1 firstly for the purpose of arresting as described above, and secondly for the purpose of providing the impact surface required for the instrument used in the installation of the implant.

[0014] According to the invention, the stem 2 is formed of at least one wing 4 extending substantially in the longitudinal direction of the body 1. Each wing 4 connected with the stem 2 is at one edge 4a attached to the outer surface of the body 1. Further, the other edge surface 4b of the wing, attached to the edge 4a in perpendicular direction, is designed to be parallel with the back surface 1a of the body 1. This back edge surface 4b of the wing is situated essentially in the same plane as the back surface 1a of the body 1 to form the above-mentioned wide impact surface required for the front surface of the instrument. The thickness of the wing 4 or the like, i.e. the dimension x does not exceed the maximum dimension V of the body 1 in the direction of dimension x.

[0015] In the embodiment shown in Fig. 1, the implant comprises two wings 4 protruding from the body 1 in the range of the stem 2 in two directions. In the embodiment shown in Fig. 1, the parts protrude radially in opposite directions as seen in the longitudinal direction of the body, whereby the wings 4 form an integrated plate-like piece having a bulge K at its centre formed by the outer surface of body 1 on both sides of the main plane of said plate-like piece.

[0016] As shown in Fig. 1, each wing 4 has substantially a quadrangular form, preferably a rectangular or trapezoid form, whereby in the direction of installation of the wing 4, the third edge 4c is substantially transverse or perpendicular to the longitudinal direction of the body 1 and thus provides an effective arresting impact at the end of the installation operation and keeps the implant in its position.

[0017] The body 1 can have a polygonal or curved cross-section, but in an advantageous embodiment, the cross-sectional form of the body is a circle with a substantially even thickness, as shown in Fig. 1. The thickness x of the wing can thus be smaller than the diameter V of the circular form. The dimension x of the wing can

have an even thickness or it can taper off or widen from the first edge 4a towards the fourth and outermost edge 4d of the wing 4.

[0018] The arresting means 5 which are particularly in combination with the sharp end 3a of the head 3 are formed in a manner that they do not completely protrude from the outer surface of the body 1. This facilitates the installation of the implant first as it moves in the installation channel of the instrument and further as it penetrates the tissue. The arresting means 5 are formed as a kind of scutellate structure, e.g. in two (or more) subsequent lines or mixed formations at certain distances on the whole perimeter of the body as shown in Fig. 1. The arresting means 5 in connection with the head 3 are formed by cuts 6 or the like made in the polymer material of the body 1, which are used for separating part of the material of the body 1 as barbs or the like, their base parts 5a being connected to the body 1 and their bodies 5b and heads 5c being directed to the stem 2 of the implant. The cuts 6 or the like are formed to comprise a first, substantially curved section 6a, where the head 5c of the said arresting means 5 is formed, and a second section 6b substantially parallel to the longitudinal direction of the body, where the body 5b of the arresting means 5 is formed. In the installed position of the implant, the arresting means 5 tend to be directed outwards from the body, if the implant is subjected to forces which tend to move it in the direction opposite to the direction of installation. Thus, the scutellate structure of the arresting means, positioned in two adjacent lines on the whole perimeter of the body in its longitudinal direction, prevents the movement of the stem in the direction opposite to the direction of installation. It is obvious that the cuts 6 can be formed by a cutting means also to be directed at an inclined angle inwards the body 1, whereby the material forming the arresting means 5 of the body 1, particularly its head 5c, bends to protrude from the outer surface of the body 1.

[0019] The arresting means 5 are thus at least partly formed by working, e.g. cutting, the material of the body 1 substantially in the longitudinal direction of the body 1. Part of the arresting means 5 can naturally be formed e.g. of structures known from US-4,873,976.

[0020] Figures 2-5 show schematically how three implants D of the type of Fig. 1 are used in fixation of a meniscal lesion L. The bodies of the implants 2 (solid lines) are on the outer (upper) surface of the meniscus. The bodies and the heads of the implants (drawn by broken lines) are inside of the meniscal tissue. Figure 3 shows in a cross-sectional side view in vertical plane in the direction x-x of Fig. 2 how a meniscal repair implant penetrates the lesion L so that its body 1 and head 3 are inside of the meniscal tissue and the stem 2 is at least partially on the surface of the meniscus. It is possible also to trigger the implant totally inside of the meniscal tissue as shown in Fig. 4. In this case, the irritation effect of the implant inside of joint cavity is minimal. In ruptures near the joint capsule NK, the head 3 can pen-

etrate through the meniscal tissue into the joint capsule NK as shown in Fig. 5.

[0021] The self-reinforced absorbable implants of this invention can be manufactured of absorbable polymers, copolymers or polymer mixtures or alloys with several methods. It is possible e.g. to use the techniques of publication U.S. Pat. No. 4,743,257 to sinter in a compression mold absorbable fibers (and possible additional binding polymer powder) together to create a self-reinforced structure. The implants of this invention can be molded ready in a single compression molding cycle, or they can be machined at least partially mechanically (and using possible additional heat) after sintering.

[0022] The self-reinforced structure can be created also during extrusion or injection moulding of absorbable polymeric melt through a suitable die or into a suitable mold at high speed and pressure. When cooling occurs at suitable conditions, the flow orientation of the melt remains in solid material as self-reinforcing structure. In an advantageous embodiment, the mold can have the form of the implant, but it is also possible to machine injection-molded or extruded semifinished products to the implants of the invention mechanically (and using possibly also heat).

[0023] The self-reinforced implants of this invention can be manufactured also by machining mechanically (and/or possibly also using heat) from self-reinforced extruded or injection-molded and drawn semifinished products, such as rods and wings described in WO 88/05312.

[0024] In some advantageous embodiments of this invention, the reinforcing elements of the self-reinforced structure are mainly oriented in the direction of the long axis of the stem of the implant. The reinforcement elements can also turn spirally around the long axis of the implant. Also other different orientations of reinforcement elements in elongated samples which are familiar from composite technology can be applied (see e.g. Engineered Materials Handbook, Volume 1, Composites, ASM International, Metals Park, Ohio 44073 USA, 1988). However, a general feature of self-reinforcement of the implants of this invention is that an essential part of reinforcing elements is oriented in such a way that they can carry effectively the different loads (such as tensile, bending and shear loads) which are directed to the healing meniscal tissue from the outside (e.g. because of the movements of the patient's knee).

[0025] According to an advantageous embodiment of the invention, the meniscal repair implant may contain one or more bioactive substances, such as antibiotics, chemotherapeutic substances, substances accelerating the healing of the wound, growth hormones etc. Such bioactive meniscal repair implants are especially advantageous in surgical use, because they contribute with biochemical, drug etc. effects to the healing of the lesion in addition to the mechanical supporting effect.

[0026] The self-reinforced materials of the implants typically have tensile strengths 100-500 MPa, bending

strengths 100-400 MPa and shear strengths 80-200 MPa. Additionally, they are usually stiff and tough. These mechanical properties are superior to those of non-reinforced absorbable polymers which typically show strengths between 40 and 100 MPa and are additionally either very flexible or brittle (see e.g. S. Vainionpää, P. Rokkanen and P. Törmälä, "Surgical Applications of Biodegradable Polymers in Human Tissues", Progr. Polym. Sci. 14 (1989), pp. 679-716).

[0027] The implants of the present invention as well as the instruments are sterilized by any of the well known sterilization techniques generally depending on the type of material used to manufacture of the implant or the instrument or its components. Suitable sterilization techniques include heat or steam sterilization, radiation sterilization such as cobalt 60 irradiation or electron beams, ethylene oxide sterilization, and the like.

[0028] After the description above of the present invention and certain specific embodiments therein, it will be readily apparent to those skilled in the art that many variations and modifications may be made to the present invention without departing from the scope thereof as defined by the appended claims. The examples below illustrate the production of implants of the invention as also the use of implants and instruments of the invention.

EXAMPLE 1.

[0029] Molds were constructed for transfer molding or for compression molding (sintering) and for injection molding of meniscal repair implants with the geometry corresponding substantially to that of the device in Fig. 1. The dimensions of the manufactured implants were: the length of the arresting means 5 connected with the head 3 in two subsequent lines: about 2.0 mm; the thickness of the cylindrical body 1: 1.4 mm; the dimension x of the wing 4: 1.1 mm; the edge 4a: 3 mm and edges 4b, 4c: 1.5 mm. The total length of the implants was 15 mm. The cuts required for formation of the arresting means 5 were made at a separate stage after the compression stage.

[0030] The implants of the invention were manufactured by transfer molding in the following manner.

[0031] The melt of glycolide/lactide (90/10) copolymer (internal viscosity $[\eta] = 1.5$ in 0.1% hexafluoroisopropanol solution ($T = 25^\circ\text{C}$)) was mixed with 8 mm long fibers of the same material. The melt-fiber mixture was injected rapidly into the implant mold which was cooled rapidly. The fiber content of the implants was 30% (w/w). The bending strength of these self-reinforced absorbable implants was 140 MPa. The bending strength of corresponding non-reinforced devices manufactured from glycolide/lactide copolymer melt was 80 MPa.

EXAMPLE 2.

[0032] The mold of Example 1 was used to manufacture implants by compression molding. Glycolide/lactide copolymer sutures (Vicryl^R) (size 2 USP) were heated in evacuated mold to 185°C during ca. 4 min which caused the partial melting of fiber units of sutures. The material was compression molded to a device of Fig. 1a with a pressure of $2 \times 10^8 \text{ Pa} \cdot \text{m}^{-2}$ (2000 bar), and it was cooled rapidly. The shear strength of these self-reinforced implants was 120 MPa. The shear strength of corresponding non-reinforced devices manufactured from glycolide/lactide copolymer melt was 70 MPa.

EXAMPLE 3.

[0033] The mold of Example 1 was used to manufacture the devices by compression molding. Polyglycolide sutures (Dexon^R) (size 2 USP) were heated in evacuated mold to 224°C during ca. 5 min with a pressure of $2 \times 10^8 \text{ Pa} \cdot \text{m}^{-2}$ (2000 bar). The softened fiber material was fused partially together, and it filled the mold cavity shaped like the implant of Fig. 1. The mold was cooled rapidly, and the implant was removed. The tensile strength of these self-reinforced absorbable devices was 160 MPa. The tensile strength of corresponding non-reinforced implants manufactured from polyglycolide melt was 80 MPa.

EXAMPLE 4.

[0034] Polyglycolide sutures (Dexon^R) (size 2 USP) were melted at $T = 230^\circ\text{C}$. The polymer melt was injected rapidly into the mold which was partially filled with continuous Dexon^R sutures. The mold was cooled rapidly. The fiber content of self-reinforced implants was 40% (w/w), and their shear strength was 120 MPa. The shear strength of corresponding non-reinforced implants manufactured from polyglycolide melt was 50 MPa.

EXAMPLE 5.

[0035] Isomers of absorbable polymers can be applied to manufacture implants of the invention. For example isomers of polylactide, such as poly-L-lactide (PLLA), poly-D-lactide (PDLA), poly-DL-lactide (PDLLA) and copolymers of L-lactide and D-lactide which contain different amounts of L-units and D-units can be used as such in fiber form, or mixtures of their fibers can be used to sinter the implants. PLLA is a partially crystalline polymer with a melting point of ca. 180°C . The isomers containing D-units have lower melting points. Therefore numerous types of self-reinforced implants can be manufactured of polylactide isomers using fibers of PLLA or of copolymer with low content of D-units as reinforcement fibers and a copolymer with higher content of D-units as matrix. The self-reinforced

materials can be manufactured of these materials e.g. by combining isomer matrix and fibers, thread or corresponding reinforcement structures to each other by means of heat and pressure.

[0036] Bundles of poly-L-lactide (PLLA) fibers (fiber diameter 120 μm , molecular weight of PLLA = 700 000) and the finely powdered DL isomer (molecular weight = 100 000) were mixed mechanically together and compression molded in mold of Example 1 at 165°C and $2 \times 10^8 \text{Pa.m}^{-2}$ (2000 bar) pressure for 5 min and cooled rapidly. The fiber content of self-reinforced implants was 50%, and their bending strength was 200 MPa. Bending strengths of non-reinforced rods manufactured from polymer melts were for PLLA 600 MPa and for poly-DL-lactide 50 MPa.

EXAMPLE 6.

[0037] Poly-L-lactide (Mw = 700 000) fibers (diameter 100 μm) were heated in pressurized mold of Example 1 to 174°C during ca. 6 min with a pressure of $2 \times 10^8 \text{Pa.m}^{-2}$ (2000 bar). The softened fiber material was partially fused together filling the mold, and the mold was cooled to room temperature rapidly. The tensile strength of these self-reinforced absorbable implants was 120 MPa. The tensile strength of corresponding non-reinforced implants manufactured from poly-L-lactide melt was 50 MPa.

EXAMPLE 7.

[0038] Poly- β -hydroxybutyric acid fibers (diameter 100 μm) were heated in pressurized mold of Example 1 to 175°C for 5 min with a pressure of $2 \times 10^8 \text{Pa.m}^{-2}$ (2000 bar). The softened fiber material was partially fused together, and the mold was rapidly cooled to room temperature. The bending strength of these self-reinforced absorbable composite devices was 100 MPa. The bending strength of corresponding non-reinforced implants manufactured of poly- β -hydroxybutyrate acid melt was 40 MPa.

EXAMPLE 8.

[0039] Polydioxanone sutures (PDS of Ethicon; size 0) were heated in pressurized mold of Example 1 to 103°C for 6 min with a pressure of $2 \times 10^8 \text{Pa.m}^{-2}$ (2000 bar). The softened fiber material was partially fused together, and the mold was rapidly cooled to room temperature. The shear strength of these self-reinforced absorbable composite implants was 140 MPa. The shear strength of corresponding non-reinforced implants manufactured of polydioxanone melt was 50 MPa.

EXAMPLE 9.

[0040] Glycolide/lactide (PGA/PLA) copolymer sutures (Vicryl[®]; size 1) containing 30% (w/w) of polyg-

lycolide sutures (Dexon[®]; size 2) were heated in mold of Example 1 in vacuum at 180°C for 6 min, which caused the partial melting of glycolide/lactide fiber units of Vicryl sutures. The material was compression molded to implants with a pressure of $2 \times 10^8 \text{Pa.m}^{-2}$ (2000 bar), and it was rapidly cooled.

[0041] A hybrid composite rod which was composed of self-reinforced glycolide/lactide material into which were embedded polyglycolide sutures was obtained. The bending strength of hybride composite material was 250 MPa. The bending strength of corresponding composite manufactured from glycolide/lactide copolymer melt reinforced with 30% (w/w) of polyglycolide sutures was 200 MPa.

EXAMPLE 10.

[0042] Monofilament sutures (size 0) manufactured of polyglycolide/trimethylenecarbonate copolymer (Maxon of Davis+Geck) were heated in a pressurized mold of Example 1 to 225°C for 4 min, applying a pressure of $2 \times 10^8 \text{Pa.m}^{-2}$ (2000 bar) during the last 1 min. The sutures were partially fused together, and the mold was rapidly cooled to room temperature. Self-reinforced absorbable devices with the shear strength of 130 MPa were obtained. The shear strength of corresponding non-reinforced implants manufactured of totally melted Maxon sutures was 60 MPa.

EXAMPLE 11.

[0043] Poly-L-lactide (PLLA; Mw = 700 000) was extruded to continuous cylindrical rods with a diameter (\varnothing) of 4 mm. The rods were drawn to the drawing ratio 10, simultaneously raising the temperature of the rods to 90...130°C. The self-reinforced (fibrillated) structure of the drawn rods was seen microscopically.

[0044] The self-reinforced rods were cut to the length of ca. 20 mm and formed to the implants of the invention by attaching the stem to one end of the rod in a heated mold ($T = 175^\circ\text{C}$) and by cutting a set of arresting means to the head as shown in Fig. 1.

[0045] The implants manufactured by the method described above showed bending strength of 250 MPa and shear strength of 170 MPa.

EXAMPLE 12.

[0046] Polyglycolide (Mw ca. 50 000) was extruded to continuous rods with a diameter of 4.4 mm. The rods were drawn at 160°C to self-reinforced rods with a diameter of 1.3 mm. The continuous rods were cut to pieces of ca. 21 mm, to which stems were formed in molds of Example 11 at 230°C and arresting means were worked in connection with the head. These implants of the invention showed bending strength of 360 MPa and shear strength of 250 MPa.

EXAMPLE 13.

[0047] Monofilament sutures (size 2; Maxon of Davis+Geck) manufactured of polyglycolide/trimethyl-
 enecarbonate copolymer were cut to 5-10 mm pieces
 and melted and extruded with a self-made piston
 extruder to a continuous rod with a diameter of 4.4 mm.
 The rod was drawn at 140...195°C to a self-reinforced
 rod with a diameter of 1.1 mm. The continuous, self-
 reinforced rod was cut to pieces of ca. 21 mm, and the
 head and stem parts were cut and formed by upsetting
 at $T = 220^{\circ}\text{C}$ with the method of Example 11. These
 devices of the invention showed shear strength of 140
 MPa.

[0048] The bending strength measurements of the
 Examples above were made with 3-point bending by
 supporting the head and the stem on specially con-
 structed supports and by bending the implant from the
 middle with a crosshead at a speed of 5 mm/min. The
 shear strength was measured from the middle of the
 implant with a punch tester.

[0049] The strength values were measured at room
 temperature (22...23°C) with a mechanical testing
 machine (by J.J. Lloyd Instruments, England).

EXAMPLE 14.

[0050] Poly-L-lactide (Mw ca. 100 000) and poly-D-
 lactide (Mw ca. 100 000) were blended in the melt state
 (blending ratio 1:1) in an extruder. This alloy was
 extruded to a rod with a 4.4 mm diameter and solidified
 to a stereocomplex material which exhibited a melting
 point of 220°C . The rod was heat treated at 180°C and
 drawn to self-reinforced rod with a diameter of 1.1 mm.
 The self-reinforced rod was cut to pieces of 21 mm.
 These were upset into the arrow-shaped implants of
 Example 13 at 220°C using the molds of Example 13.
 These implants showed the bending strength of 280
 MPa. The non-reinforced injection-molded rods showed
 the bending strength of 120 MPa.

EXAMPLE 15.

[0051] The poly-L-lactide and poly-D-lactide blend of
 Example 14 was extruded to 0.8 mm thick monofila-
 ments which were drawn to fibers with a diameter of 100
 μm at 110°C . The stereocomplex fibers were sintered
 into the devices of the invention in a compression mold
 by heating them for 5 min from 23°C to 222°C at a pres-
 sure of $2 \times 10^8 \text{ Pa} \cdot \text{m}^2$ (2000 bar) These self-reinforced
 polylactide stereocomplex implants showed the shear
 strength of 220 MPa. The corresponding implants man-
 ufactured by injection molding of the same poly-L-lac-
 tide and poly-D-lactide melt showed the shear strength
 of 95 MPa.

EXAMPLE 16.

[0052] Several types of self-reinforced implants with
 the dimensions of the implants of Example 1 were man-
 ufactured by methods according to Examples 1-15 and
 triggered into cadaver meniscal tissue obtained from
 sheep by a method disclosed in an invention "Surgical
 installation instrument" parallel to the present invention
 (PCT/FI93/00015).

A preliminary hole (length ca. 15 mm) was made into
 the tissue with a steel punch with a diameter of 1.2 mm
 at an angle of approximately 45° against the surface of
 the meniscus. The end of the head of the implant was
 carefully penetrated into the preliminary hole, and the
 implant was triggered to the preliminary hole in the
 meniscus. When testing each implant material, five par-
 allel implants were applied. All the self-reinforced
 implants manufactured according to Examples 1-4, 6, 9,
 11, 12 and 14 sunk well into the meniscus without
 breaking or bending. A total of 7 implants made accord-
 ing to Examples 5, 7, 8, 10 and 13 buckled or bent and
 did not sink properly into the meniscus. However, they
 did not break.

[0053] Comparative triggering tests were made with
 injection-molded, non-reinforced implants manufac-
 tured according to Examples 1-10. Twenty-one of the
 implants buckled and/or broke (depending on the raw
 material) during triggering.

[0054] These cadaver studies showed that the self-
 reinforced implants of the invention did not break during
 triggering them into meniscal tissue. The triggering
 method shown in the present application is thus suitable
 for them. On the contrary, many of the non-reinforced
 implants were broken and therefore they cannot be
 applied with the easy and rapid triggering method.

EXAMPLE 17.

[0055] Implants of the invention according to the
 dimensions of Example 1 were used in experimental fix-
 ation of surgically generated meniscal lesions in sheep.
 The following self-reinforced (SR) implants were used:
 SR-PGA implants of Example 3, SR-PGA implants of
 Example 4, SR-PLLA implants of Example 6, SR-
 PGA/PLA implants of Example 9, SR-PLLA implants of
 Example 11, SR-PGA implants of Example 12, and
 polylactide-stereocomplex implants of Example 15. Two
 animals were operated in each case. The devices were
 applied through an arthrotomy under direct visualization
 in surgically generated meniscal lesions by triggering
 them with the instrument of the invention into the menis-
 cal tissue. No fracture, buckling or unfavorable migration
 of implants occurred during operations. Two control ani-
 mals were used where lesion was not repaired. After 12
 weeks, the animals were killed and the menisci were
 examined. The controls showed uncontrolled healing
 and displacement of the meniscal tissue. Most (ca.
 80%) of the menisci treated with devices of the invention

had healed well with a fibrous healing through the lesion.

Claims

1. A surgical implant formed in the shape of an arrow and made of a polymer or polymeric compound which is substantially absorbable in tissue conditions, said implant comprising a body (1) extending along a longitudinal direction, a head portion (3) at a first end of said body, a tail portion (2, 4) connected by an edge portion thereof (4a) to a second end of said body and protruding perpendicularly with respect to the longitudinal direction of the body, and arresting means (5) for arresting said implant in position, according to the use of the implant, in a direction substantially opposite to the direction of installation thereof, characterized in that said tail portion (2) is formed of at least one wing (4), each wing being defined by substantially planar major surfaces extending substantially parallel to a plane containing the longitudinal direction of said body (1), and in that said body contains a reinforcement structure made of a polymer or polymeric compound.
2. Implant according to claim 1, wherein said arresting means (5) are comprised of portions of said body (1) which are cut in a direction substantially parallel and/or diagonally with respect to said body such as to present a free end (5c) and an end (5a) contiguous with said body.
3. Implant according to claim 1 or 2, wherein the thickness dimension (x) of the wing (4) does not exceed the maximum dimension (V) of the body (1) in the direction of the thickness dimension (x).
4. Implant according to any one of claims 1 to 3, wherein there are at least two wings (4) protruding from the body (1) in two or more directions respectively.
5. Implant according to any of the claims 1 to 4, wherein there are two wings (4), protruding in opposite directions from the body (1).
6. Implant according to any of the claims 1 to 5, wherein the or each wing (4) has a polygonal, substantially quadrangular and preferably a rectangular shape; the back edge surface (4b) of said wing(s) (4) which is connected to the back surface (1a) of the body (1) is in the same plane as the said back surface (1a); and the front edge (4c) of the wing(s) (4) is transverse to the longitudinal direction of the body (1).
7. Implant according to any of the claims 1 to 6,

wherein the cross-section of the body (1) is substantially polygonal or curved, or preferably circular with even dimensions in the longitudinal direction of the body (1), and the thickness dimension (x) of the wing(s) (4) is smaller than the diameter (V) of the said cross-section.

8. Implant according to any of the claims 1 to 7, wherein the wing(s) (4) has (have) substantially an even thickness.
9. Implant according to any one of claims 1 to 8, wherein the arresting means (5) are formed as a scutellate structure in the body (1), substantially on the whole perimeter of the body (1), in connection with the head (3).
10. Implant according to claim 9, wherein the arresting means (5), in connection with the head (3), are formed by cuts (6) made in the material of the body (1), which are used for separating part of the material of the body as barbs connected with the body (1), their bodies (5b) and heads (5c) being directed towards the tail portion (2) of the implant, whereby the said barbs form the said scutellate structure in line and/or random order.
11. Implant according to claim 9, wherein the cuts (6) are at least in some arresting means (5) formed in a manner that they comprise a first substantially curved section (6a), where the head (5c) of the said arresting means is formed, and a second section (6b) substantially parallel to the longitudinal direction of the body, where the body (5b) of the arresting means (5) is formed, or wherein the cuts (6) are in at least some arresting means (5) substantially straight cuts diagonally directed towards the inside of the body (1).

Patentansprüche

1. Chirurgisches Implantat, das in Form eines Pfeiles ausgebildet ist und aus einem Polymer oder einer polymeren Verbindung hergestellt ist, das bzw. die in Gewebeumgebungen im wesentlichen absorbierbar ist, wobei das Implantat einen sich in Längsrichtung erstreckenden Körper (1), einen Kopfbereich (3) an einem ersten Ende des Körpers, einen Endbereich (2, 4), der durch einen Randbereich (4a) mit einem zweiten Ende des Körpers verbunden ist und in bezug auf die Längsrichtung des Körpers rechtwinklig wegragt, sowie Arretiereinrichtungen (5) zum Arretieren des Implantats in seiner Position nach Maßgabe der Verwendung des Implantats in einer zu der Installationsrichtung des Implantats im wesentlichen entgegengesetzten Richtung aufweist, dadurch gekennzeichnet, daß der Endbereich (2)

aus wenigstens einem Flügel (4) gebildet ist, wobei jeder Flügel durch im wesentlichen planare Hauptflächen gebildet ist, die sich im wesentlichen parallel zu einer die Längsrichtung des Körpers (1) enthaltenden Ebene erstrecken, und daß der Körper eine Verstärkungsstruktur enthält, die aus einem Polymer oder einer polymeren Verbindung gebildet ist.

2. Implantat nach Anspruch 1, wobei die Arretiereinrichtungen (5) aus Bereichen des Körpers (1) gebildet sind, die in einer zu dem Körper im wesentlichen parallelen und/oder diagonalen Richtung geschnitten sind, so daß sie ein freies Ende (5c) und ein mit dem Körper kontinuierlich ausgebildetes Ende (5a) aufweisen.
3. Implantat nach Anspruch 1 oder 2, wobei die Dickenabmessung (x) des Flügels (4) die maximale Abmessung (V) des Körpers (1) in Richtung der Dickenabmessung (x) nicht übersteigt.
4. Implantat nach einem der Ansprüche 1 bis 3, wobei wenigstens zwei Flügel (4) vorhanden sind, die von dem Körper (1) in zwei bzw. mehr Richtungen wegragen.
5. Implantat nach einem der Ansprüche 1 bis 4, wobei zwei Flügel (4) vorhanden sind, die in entgegengesetzten Richtungen von dem Körper (1) wegragen.
6. Implantat nach einem der Ansprüche 1 bis 5, wobei der oder jeder Flügel (4) eine polygonale, im wesentlichen viereckige und vorzugsweise rechteckige Formgebung aufweist; wobei die mit der rückwärtigen Fläche (1a) des Körpers (1) verbundene rückwärtige Randfläche (4b) des Flügels oder der Flügel (4) in derselben Ebene liegt wie die rückwärtige Fläche (1a); und wobei der vordere Rand (4c) des Flügels oder der Flügel (4) quer zu der Längsrichtung des Körpers (1) ist.
7. Implantat nach einem der Ansprüche 1 bis 6, wobei die Querschnittsfläche des Körpers (1) im wesentlichen polygonal oder gekrümmt ist oder vorzugsweise kreisförmig mit gleichförmigen Abmessungen in der Längsrichtung des Körpers (1) ist und wobei die Dickenabmessung (x) des Flügels oder der Flügel (4) kleiner ist als der Durchmesser (V) der genannten Querschnittsfläche.
8. Implantat nach einem der Ansprüche 1 bis 7, wobei der Flügel oder die Flügel (4) im wesentlichen eine gleichmäßige Dicke aufweist bzw. aufweisen.
9. Implantat nach einem der Ansprüche 1 bis 8,

wobei die Arretiereinrichtungen (5) als schuppenförmiges Gebilde an dem Körper (1) im wesentlichen um den gesamten Umfang des Körpers (1) in Verbindung mit dem Kopf (3) ausgebildet sind.

10. Implantat nach Anspruch 9, wobei die Arretiereinrichtungen (5) in Verbindung mit dem Kopf (3) durch Schnitte (6) gebildet sind, die in das Material des Körpers (1) eingebracht sind und zum Trennen eines Teils des Materials des Körpers nach Art von mit dem Körper (1) verbundenen Widerhaken verwendet werden, wobei ihre Körper (5b) und Köpfe (5c) in Richtung auf den Endbereich (2) des Implantats gerichtet sind, wodurch die genannten Widerhaken die genannte schuppenförmige Struktur in Reihenordnung und/oder in unregelmäßiger Anordnung bilden.
11. Implantat nach Anspruch 9, wobei die Schnitte (6) wenigstens in einigen Arretiereinrichtungen (5) in einer derartigen Weise ausgebildet sind, daß sie einen ersten, im wesentlichen gekrümmten Abschnitt (6a), an dem der Kopf (5c) der Arretiereinrichtungen gebildet ist, sowie einen zweiten Abschnitt (6b) im wesentlichen parallel zu der Längsrichtung des Körpers aufweisen, an dem der Körper (5b) der Arretiereinrichtungen gebildet ist, oder wobei es sich bei den Schnitten (6) in wenigstens einigen Arretiereinrichtungen (5) um im wesentlichen gerade Schnitte handelt, die diagonal in Richtung auf das Innere des Körpers (1) weisen.

Revendications

1. Implant chirurgical formé sous la forme d'une flèche et constitué par un polymère ou composé polymérique qui est sensiblement absorbable dans les conditions tissulaires, ledit implant comprenant un corps (1) qui s'étend dans une direction longitudinale, une partie formant tête (3) au niveau d'une première extrémité dudit corps, une partie formant queue (2, 4) reliée par une partie (4a) formant bord de celle-ci à une seconde extrémité dudit corps et qui fait saillie perpendiculairement à la direction longitudinale du corps, et des moyens de retenue (5) pour retenir ledit implant en position, selon l'utilisation de l'implant, dans un sens sensiblement opposé au sens de son installation, caractérisé en ce que ladite partie formant queue (2) est formée d'au moins une aile (4), chaque aile étant définie par des surfaces principales sensiblement planes qui s'étendent sensiblement parallèlement à un plan contenant la direction longitudinale dudit corps (1), et en ce que ledit corps contient une structure de renforcement constituée par un polymère ou composé polymérique.

2. Implant selon la revendication 1, dans lequel lesdits

moyens de retenue (5) sont constitués par des parties dudit corps (1) qui sont découpées dans une direction sensiblement parallèle et/ou diagonale audit corps de manière à présenter une extrémité libre (5c) et une extrémité (5a) contiguë audit corps.

3. Implant selon la revendication 1 ou 2, dans lequel la dimension de l'épaisseur (x) de l'aile (4) ne dépasse pas la dimension maximale (V) du corps (1) dans la direction de la dimension de l'épaisseur (x). 10
4. Implant selon l'une quelconque des revendications 1 à 3, dans lequel il y a au moins deux ailes (4) qui font saillie du corps (1) dans deux ou plusieurs directions respectivement. 15
5. Implant selon l'une quelconque des revendications 1 à 4, dans lequel il y a deux ailes (4) qui font saillie dans des directions opposées depuis le corps (1). 20
6. Implant selon l'une quelconque des revendications 1 à 5, dans lequel la ou chaque aile (4) a une forme polygonale, sensiblement quadrangulaire et de préférence rectangulaire, la surface du bord arrière (4b) de ladite aile (4) ou desdites ailes (4) qui est reliée à la surface arrière (1a) du corps (1) est dans le même plan que ladite surface arrière (1a), et le bord avant (4c) de l'aile (4) ou des ailes (4) est transversale à la direction longitudinale du corps (1). 25
30
7. Implant selon l'une quelconque des revendications 1 à 6, dans lequel la section droite du corps (1) est sensiblement polygonale ou incurvée, ou de préférence circulaire avec des dimensions uniformes dans la direction longitudinale du corps (1), et la dimension de l'épaisseur (x) de l'aile (4) ou des ailes (4) est inférieure au diamètre (V) de ladite section droite. 35
40
8. Implant selon l'une quelconque des revendications 1 à 7, dans lequel l'aile (4) ou les ailes (4) a ou ont une épaisseur sensiblement uniforme. 45
9. Implant selon l'une quelconque des revendications 1 à 8, dans lequel les moyens de retenue (5) sont formés sous forme d'une structure scutelliforme dans le corps (1), sensiblement sur tout le périmètre du corps (1), en liaison avec la tête (3). 50
10. Implant selon la revendication 9, dans lequel les moyens de retenue (5), en liaison avec la tête (3), sont formés par des découpures (6) pratiquées dans le matériau du corps (1), qui sont utilisées pour séparer une partie du matériau du corps sous forme de barbelures reliées au corps (1), leurs corps (5b) et leurs têtes (5c) étant dirigés vers la 55

partie formant queue (2) de l'implant, de sorte que lesdites barbelures forment ladite structure scutelliforme en ligne et/ou dans un ordre aléatoire.

11. Implant selon la revendication 9, dans lequel les découpures (6) sont formées, au moins dans certains moyens de retenue (5), d'une manière qu'elles comprennent une première section sensiblement incurvée (6a) où est formée la tête (5c) desdits moyens de retenue, et une seconde section (6b) sensiblement parallèle à la direction longitudinale du corps où est formé le corps (5b) des moyens de retenue (5), ou dans lequel, dans au moins certains moyens de retenue (5), les découpures (6) soit des découpures sensiblement rectilignes dirigées diagonalement vers l'intérieur du corps (1).








Fig 1

THIS PAGE BLANK (USPTO)



THIS PAGE BLANK (USPTO)